



REINFORCING
SUCCESS

PRODUCT DATA SHEET WINFAB® 2505



FILTRATION



SEPARATION

WINFAB® 2505 geotextile fabric is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position.


WINFAB® 2505 geotextile fabric resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Tensile Strength (Grab)	ASTM D4632	375 x 375 lbs	1,669 x 1,669 N
Elongation (Grab)	ASTM D4632	15% x 8%	15% x 8%
Trapezoidal Tear Strength	ASTM D4533	120 x 120 lbs	534 x 534 N
CBR Puncture	ASTM D6241	1200 lbs	5,340 N
UV Resistance (500 hrs)	ASTM D4355	70%	70%
Apparent Opening Size*	ASTM D4751	50 US Std. Sieve	0.3 mm
Permittivity	ASTM D4491	0.2 sec ⁻¹	0.2 sec ⁻¹
Water Flow Rate	ASTM D4491	15 gpm/ft ²	611 lpm/m ²

*Maximum Average Roll Value

PROPERTY	TYPICAL ENGLISH	TYPICAL METRIC
Roll Dimensions	15 x 300 ft	4.6 x 91.5 m

Disclaimer: WINFAB assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. WINFAB disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

WINFAB® &  are trademarks of Willacoochee Industrial Fabrics, Inc.

©2021 Willacoochee Industrial Fabrics Inc.

WINFAB | www.winfabusa.com
1 Nashville Mills Rd. Nashville GA 31639
Ph: (912) 534-5757 • Fax: (912) 534-5533

